

Wieland-M58

CuZn42 – CW510L
Lead-free brass

Extruded and drawn products



Material designation	
EN	CuZn42 – CW510L
UNS	no EN standard

Chemical composition*	
Cu	58 %
Zn	balance
Pb	max. 0.009 %

* Reference values in % by weight

Physical properties*		
Electrical conductivity	MS/m %IACS	18 31
Thermal conductivity	W/(m·K)	139
Thermal expansion coefficient (0–300 °C)	10 ⁻⁶ /K	21.7
Density	g/cm ³	8.36
Modulus of elasticity	GPa	107

* Reference values at room temperature

Corrosion resistance

Machining brass is generally quite resistant against organic substances as well as neutral or alkaline compounds. Stress corrosion cracking should be taken into account, especially in an ammoniacal atmosphere and whilst under mechanical stress. Dezincification in warm, acidic waters should also be taken into consideration.

Product standards	
Rod	EN 12164
	EN 12165
Wire	EN 12166

Material properties and typical applications

Wieland-M58 is a lead-free material which nevertheless has good machining properties due to its microstructure. M58 can therefore be used as a substitute for conventional lead-containing machining brass if a lead content of ≤ 90 ppm is necessary and the requirements regarding mechanical properties and corrosion resistance are not too high.

The material composition meets the requirements of the CPSIA.

Types of delivery

The Extruded and Drawn Products Division supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

Fabrication properties

Forming		Surface treatment	
Machinability (CuZn39Pb3 = 100 %)	50 %	Polishing	
Capacity for being cold worked	poor	mechanical	good
Capacity for being hot worked	excellent	electrolytic	poor
		Electroplating	excellent
Joining		Heat treatment	
Resistance welding (butt weld)	fair	Melting range	870–900 °C
Inert gas shielded arc welding	fair	Hot working	650–750 °C
Gas welding	fair	Soft annealing	450–550 °C 1–3 h
Hard soldering	excellent	Thermal stress relieving	250–350 °C 1–3 h
Soft soldering	excellent		

Wieland-M58

CuZn42

Lead-free brass

Mechanical properties according to EN

Round rods/polygonal rods acc. to EN 12164

Temper	Diameter		Width across flats		Tensile strength	Yield strength		Elongation			Hardness	
	mm from	mm to	mm from	mm to	R _m MPa min.	R _{p0.2} MPa min. MPa max.		A100 %	A11,3 %	A %	HB	
M	all		all		as manufactured – without specified mechanical properties							
R360	6	80	5	60	360	–	320	–	15	20	–	–
H090	6	80	5	60	–	–	–	–	–	–	90	125
R430	2	40	2	35	430	220	–	6	8	10	–	–
H110	2	40	2	35	–	–	–	–	–	–	110	160
R500	2	14	2	10	500	350	–	–	3	5	–	–
H135	2	14	2	10	–	–	–	–	–	–	135	–

Round wires acc. to EN 12166

Temper	Diameter		Tensile strength	Yield strength		Elongation			Hardness		
	mm from	mm to	R _m MPa min.	R _{p0.2} MPa min. MPa max.		A100 %	A11,3 %	A %	HB		
M	all		as manufactured – without specified mechanical properties								
R360	6	20	360	–	320	–	15	20	–	–	
H095	6	20	–	–	–	–	–	–	95	130	
R430	0.5	14	430	220	–	6	8	10	–	–	
H115	1.5	14	–	–	–	–	–	–	115	170	
R500	0.5	8	500	350	–	2	5	–	–	–	
H145	1.5	8	–	–	–	–	–	–	145	–	