

Wieland-SW1
CuZn21Si3P
Lead-free special brass

**Extruded and
drawn products**



Material designation	
EN	CuZn21Si3P/CW724R
UNS	C69300

Chemical composition*	
Cu	76 %
Si	3 %
P	0,05 %
Zn	balance
Pb	max. 0,09 %

* Reference values in % by weight

Physical properties*		
Electrical conductivity	MS/m	4,5
	%IACS	7,8
Thermal conductivity	W/(m·K)	35
Density	g/cm ³	8,25
Modulus of elasticity	GPa	ca. 100

* Reference values at room temperature

Corrosion resistance

Special brass generally exhibits good corrosion resistance due to alloying additions. The addition of silicon improves resistance to tarnishing and reduces the risk to stress corrosion cracking and dezincification. For operations at temperatures >600 °C we recommend a heat treatment at 550–580 °C for 2–3 hours to optimise corrosion resistance.

Product standards	
Rod	EN 12163 EN 12164
Wire	EN 12166
Section	EN 12167

Material properties and typical applications

Wieland-SW1 is according to ELV and RoHs a lead-free special brass resisting high load and exhibiting good corrosion resistance as well as excellent machinability. This alloy is suited to the production of machined and drop forged parts. ECOBRASS is available as machining brass as well as in hot stamping quality. This material is also marketed under the designation CUPHIN for sanitary applications. The material meets the requirements of ISO 6509 regarding the dezincification resistance. Material accepted for products in contact with drinking water as per 4 MS positive list.

Types of delivery

The Extruded and Drawn Products Division supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

Fabrication properties

Forming		Surface treatment	
Machinability (CuZn39Pb3 = 100 %)	80 %	Polishing	
Capacity for being cold worked	good	mechanical	good
Capacity for being hot worked	excellent	electrolytic	poor
		Electroplating	good*

* For further fabrication properties, please contact our Technical Marketing.

Joining

Resistance welding (butt weld)	good*
Inert gas shielded arc welding	good*
Gas welding	good*
Hard soldering	good*
Soft soldering	good

* see section „Corrosion resistance“

Heat treatment

Melting range	860–925 °C
Hot working	680–750 °C
Soft annealing	550–580 °C 1–3 h

Trademarks



Further information is provided in the brochure on Ecobass.

Wieland-SW1

CuZn21Si3P
Lead-free special brass

Mechanical properties according to EN

Round rods/polygonal rods acc. to EN 12163

Temper	Diameter		Width across flats		Tensile strength		Yield strength			Elongation			Hardness	
	mm from	mm to	mm from	mm to	R _m MPa min.	R _{p0.2} MPa min.	MPa max.	A100 % min.	A11.3 % min.	A % min.	HB			
M	all		all		as manufactured – without specified mechanical properties									
R500	6	80	35	80	500	–	450	–	13	15	–	–		
H130	6	80	35	80	–	–	–	–	–	–	130	180		
R600	10	40	15	40	600	300	–	–	–	12	–	–		
H150	10	40	15	40	–	–	–	–	–	–	150	220		
R670	2	20	2	15	670	400	–	8	9	10	–	–		
H170	2	20	2	15	–	–	–	–	–	–	170	–		

Round rods/polygonal rods acc. to EN 12164

Temper	Diameter		Width across flats		Tensile strength		Yield strength			Elongation			Hardness	
	mm from	mm to	mm from	mm to	R _m MPa min.	R _{p0.2} MPa min.	MPa max.	A100 % min.	A11.3 % min.	A % min.	HB			
M	all		all		as manufactured – without specified mechanical properties									
R500	6	80	35	80	500	–	450	–	–	15	–	–		
H130	6	80	35	80	–	–	–	–	–	–	130	180		
R600	10	40	15	40	600	300	–	–	–	12	–	–		
H150	10	40	15	40	–	–	–	–	–	–	150	220		
R670	2	20	2	15	670	400	–	8	9	10	–	–		
H170	2	20	2	15	–	–	–	–	–	–	170	–		

Rectangular rods acc. to EN 12167

Temper	Width across flats		Tensile strength		Yield strength			Elongation			Hardness	
	mm from	mm to	R _m MPa min.	R _{p0.2} MPa min.	MPa max.	A100 % min.	A11.3 % min.	A % min.	HB			
M	all		as manufactured – without specified mechanical properties									
R500	2	20	500	–	450	12	13	15	–	–		
H130	2	20	–	–	–	–	–	–	130	170		
R600	2	20	600	300	–	–	11	12	–	–		
H150	2	20	–	–	–	–	–	–	150	190		
R670	2	7	670	400	–	8	9	10	–	–		
H170	2	7	–	–	–	–	–	–	170	220		

Round wires acc. to EN 12166

Temper	Diameter		Tensile strength		Yield strength			Elongation			Hardness	
	mm from	mm to	R _m MPa min.	R _{p0.2} MPa min.	MPa max.	A100 % min.	A11.3 % min.	A % min.	HB			
M	all		as manufactured – without specified mechanical properties									
R500	0.5	20	500	–	450	12	13	15	–	–		
H110	1.5	20	–	–	–	–	–	–	110	170		
R600	0.5	8	600	300	–	10	11	12	–	–		
H130	1.5	8	–	–	–	–	–	–	130	190		
R670	0.5	8	670	400	–	8	9	10	–	–		
H160	1.5	8	–	–	–	–	–	–	160	220		
R750	0.5	8	750	450	–	2	3	–	–	–		
H200	1.5	8	–	–	–	–	–	–	200	–		

Wieland-Werke AG www.wieland.com

Graf-Arco-Str. 36, 89079 Ulm, Germany, Phone +49 (0)731 944-0, Fax +49 (0)731 944-2772, info@wieland.de

This leaflet is for your general information only and is not subject to revision. No claims can be derived from it unless there is evidence of intent or gross negligence. The data presented is not guaranteed and does not replace expert advice.