

# Material data sheet

## EN AW 6082 [EN AW-Al Si1MgMn]

Compliance with the requirements of the EU directives RoHS 2011/65/EU and ELV 2000/53/EC

### 1 ) Chemical composition according to DIN EN 573-3 [% by mass, remainder Al]

| %           | Si  | Fe   | Cu   | Mn   | Mg  | Cr   | Ni | Zn   | Ti   | Bi | Pb | Each |
|-------------|-----|------|------|------|-----|------|----|------|------|----|----|------|
| <b>min.</b> | 0.7 | -    | -    | 0.40 | 0.6 | -    | -  | -    | -    | -  | -  | -    |
| <b>max.</b> | 1.3 | 0.50 | 0.10 | 1.0  | 1.2 | 0.25 | -  | 0.20 | 0.10 | -  | -  | 0.15 |

### 2 ) Mechanical properties according to DIN EN 485-2

| Temper      | Dimensions in mm |                | R <sub>m</sub> Mpa |      | R <sub>p0,2</sub> |      | A% min. | A <sub>50mm</sub> % | HBW           |
|-------------|------------------|----------------|--------------------|------|-------------------|------|---------|---------------------|---------------|
|             | D <sup>a</sup>   | S <sup>b</sup> | min.               | max. | min.              | max. | min.    | min.                | Typical value |
| <b>T6</b>   | ≥0,4             | 1,5            | 310                | -    | 260               | -    | -       | 6                   | 94            |
| <b>T651</b> | 1,5              | 3,0            | 310                | -    | 260               | -    | -       | 7                   | 94            |
| <b>T62</b>  | 3,0              | 6,0            | 310                | -    | 260               | -    | -       | 10                  | 94            |
|             | 6,0              | 12,5           | 300                | -    | 255               | -    | -       | 9                   | 91            |
|             | 12,5             | 60,0           | 295                | -    | 240               | -    | 8       | -                   | 89            |
|             | 60,0             | 100,0          | 295                | -    | 240               | -    | 7       | -                   | 89            |
|             | 100,0            | 150,0          | 275                | -    | 240               | -    | 6       | -                   | 84            |
|             | 150,0            | 175,0          | 275                | -    | 230               | -    | 4       | -                   | 83            |
|             | 175,0            | 350,0          | 260                | -    | 220               | -    | 2       | -                   | -             |

D<sup>a</sup> = Diameter for round rod / S<sup>b</sup> = Width across flat for square and hexagonal rod, Thickness for rectangular rod / c Properties may be obtained by press quenching.

Classification: 1=very good / 6=insufficient

| Physical properties   |         | General properties  |  |  |      |
|---|---------|---|--|--|------|
| Density g/cm <sup>3</sup>                                       | 2.70    | <b>Corrosion resistance to</b><br>atmospheric influences 1<br>seawater 2<br><br><b>Brazeability:</b><br>Brazing with flux 2<br>Brazing without flux 4<br>Friction soldering 2<br>Soft soldering with flux 3 | <b>Surface treatment</b><br>Protection anodizing 1<br>Decorative anodizing 3<br>Painting/Coating 2 |  |      |
| Modulus of elasticity MPa                                       | 70000   |   |  |  |      |
| Thermal conductivity W/(m K)                                    | 170-220 |   |  |  |      |
| Coefficient of thermal expansion (20-100 °) 10 <sup>-6</sup> /K | 23.4    |   |  |  |      |
| Electrical conductivity MS/m                                    | 24-32   |   |  |  |      |
| Weldability   |         | Machining properties  |  |  |      |
| Gas   | 3       | Bending   |  |  | 2    |
| TIG   | 2       | Spinning  |  |  | 3    |
| MIG   | 1       | Deep drawing up to (temper)   |  |  | 2(O) |
| Resistance fusion welding                                       | 3       |   |  |  |      |

Errors and changes excepted/This document is not subject to revision.