wieland

eco KS2

CuSP | Free-cutting copper, lead free acc. to RoHS

Material designation						
EN CuSP						
	CW114C					
UNS	C14700					

Chemical composition*					
Cu	balance				
S	0.2-0.5 %				
Р	0.003-0.005%				
Pb	< 0.1000%				

*Reference values in % by weight

Physical properties*						
Electrical	MS/m	52				
conductivity	%IACS	90				
Thermal conductivity	W/(m·K)	374				
Thermal expansion						
coefficient						
(0-300 °C)	10 ⁻⁶ /K	17.6				
Density	g/cm³	8.9				
Modulus of elasticity	GPa	118				
*Reference values at room temperature						

Material properties and typical applications

Eco KS2 is a free-cutting lead-free material with good machinability and very high electrical conductivity. It is particularly suitable for turned connectors and other electronic applications. Other typical applications are mechanical engineering components and welding torch nozzles. The addition of sulphur ensures short chips during machining. It is suited as alternative to the well established Wieland KC1 – CuPb1P. The material is lead free according to RoHS and ELV.

Types of delivery

The Extruded and Drawn Products Division supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

Fabrication properties						
Forming						
Machinability (CuZn39Pb3 = 100 %)	80 %					
Capacity for being cold worked	excellent					
Capacity for being hot worked	fair					

mechanical electrolytic Electroplating	good good good
Heat treatment	
Melting range	1,067–1,079 °C

Surface treatment

Polishing

Corrosion resistance

Generally good corrosion resistance, also in industrial athmosphere and marine air, insensitive to stress corrosion cracking.

Resistance welding (butt weld) Inert gas shielded

Joining

arc welding	
Gas welding	poor
Hard soldering	good
Soft soldering	excellent

good

poor

Heat treatment	
Melting range	1,067–1,079 °C
Hot working	750–875 °C
Soft annealing	400–450 °C 1–3 h
Thermal stress-relieving	225–275 °C 1–3 h

Product standards					
Rod	EN 12164				
Wire	FN 12166				

Trademarks

wieland ecoline **O**WICONNEC°

eco KS2

CuSP | Free-cutting copper, lead free acc. to RoHS

Dimensions and mechanical properties according to standards

Round rods/polygonal rods acc. to EN 12164											EN 12164	
Temper	Diameter Width across flat Tensile strengh R _m Yield strength R _{p0.2} Elongation %								Hardness			
	mm		mm		MPa	MPa		A100	A11,3	А	НВ	
	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.
Μ	ć	all		all	as manı	ufactured –	without s	pecified	mechar	nical prop	perties	
R250	2	80	2	80	250	180	-	3	5	7	-	-
H080	2	80	2	80	-	-	-	-	-	-	80	110
R300	2	20	2	20	300	240	-	2	3	5	-	-
H095	2	20	2	20	-	-	-	-	-	-	95	130
R360	2	10	2	10	360	300	-	-	-	-	-	-
H120	2	10	2	10	-	-	-	-	-	-	120	-

Dimensions and mechanical properties according to standards

Wires acc. to EN 12166									
Temper	Diamete	er	Tensile strength R _m	Yield strength $R_{p0,2}$	Elongation %	Hardness			
	mm		MPa	MPa	A100	A11.3	А	HV	
	from	to	min.	min.	min.	min.	min.	min.	max.
М	i	all all			as manufactured – without specified mechanical properties				
R250	1,5	12	250	180	2	4	7	-	-
H090	1,5	12	-	-	-	-	-	90	130
R300	1,5	12	300	240	-	3	5	-	-
H110	1,5	12	-	-	-	-	-	110	140
R360	1,5	10	360	360	-	-	-	-	-
H120	1,5	10	-	-	-	-	-	120	-

Wieland-Werke AG | Graf-Arco-Straße 36 | 89079 Ulm | Germany info@wieland.com | wieland.com