

eco M57

CuZn42 | Low leaded brass

Material designation

EN	CuZn42
	CW510L
UNS	not standardized

Chemical composition*

Cu	58 %
Zn	balance
Pb	0.2 %

^{*}Reference values in % by weight

Material properties and typical applications

Eco M57 is a low leaded material which is however quite suitable for machining due to its structural constitution. Eco M57 can be therefore used as a cost-effective replacement for conventional lead-containing machining brass provided that it must not meet high requirements as regards mechanical properties and corrosion resistance.

Material accepted for products in contact with drinking water as per 4 MS positive list.

Physical properties*

Electrical	MS/m	13.9
conductivity	%IACS	24
Thermal conductivity	$W/(m \cdot K)$	139
Thermal expansion		
coefficient		
(0-300 °C)	10 ⁻⁶ /K	21.7
Density	g/cm³	8.41
Moduls of elasticity	GPa	107

^{*}Reference values at room temperature

Types of delivery

The BU Extruded Products supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

Fabrication properties			
Forming		Surface treatment	
Machinability (CuZn39Pb3 = 100 %)	70 %	Polishing mechanical	good
Capacity for being	poor	electrolytic	poor
cold worked		Electroplating	excellent
Capacity for being hot worked	excellent		

Corrosion resistance

Machining brass is generally quite resistant against organic substances as well as neutral or alkaline compounds.

Stress corrosion cracking should be taken into account, especially in an ammoniacal atmosphere and whilst under mechanical stress. Dezincification in warm, acidic waters should also be taken into consideration.

Joining	
Resistance welding (butt weld)	fair
Inert gas shielded arc welding	fair
Gas welding	fair
Hard soldering	excellent

Heat treatment	
Melting range	870-900 °C
Hot working	650-750 °C
Soft annealing	450-550 °C
	1-3 h
Thermal	250-350 °C
stress relieving	1-3 h

Product standards

Rod	EN 12164
	EN 12165
Wire	FN 12166

Handelsmarken

Soft soldering

wieland ecoline

excellent

eco M57

CuZn42 | Low leaded brass

Mechani	cal pro _l	oerties :	according	to EN								
Round rods/polygonal rods acc. to EN 121									N 12164			
Temper	Diame	ter	Width a	cross flats	Tensile strength R _m	Yield st	rength R _{p0.2}	Elonga	ation %		Hardness	
	mm		mm		MPa	MPa MPa		A100	A100 A11.3 A		НВ	
	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.
М	ć	all		all	as manufactured – without specified mechanical properties							
R360	6	80	5	60	360	-	320	-	15	20	-	-
H090	6	80	5	60	-	-	-	-	-	-	90	125
R430	2	40	2	35	430	220	_	6	8	10	_	_
H110	2	40	2	35	-	-	-	-	-	-	110	160
R500	2	14	2	10	500	350	_	_	3	5	-	-
H135	2	14	2	10	-	-	-	-	-	-	135	-

Round wires acc. to EN 1210										N 12166	
Temper	Diameter		Tensile strength R _m	Tensile strength R_m Yield strength $R_{p0.2}$			Elongation %			Hardness	
	mm		MPa	MPa	МРа		A11.3	Α	НВ		
	from	to	min.	min.	max.	min.	min.	min.	min.	max.	
М		all	as m	as manufactured – without specified mechanical properties							
R360	6	20	360	_	320	_	15	20	_	_	
H095	6	20	-	-	-	-	-	-	95	130	
R430	0.5	14	430	220	_	6	8	10	_	_	
H115	1.5	14	-	-	-	-	-	-	115	170	
R500	0.5	8	500	350	_	2	5	-	-	_	
H145	1.5	8	-	-	-	_	_	_	145	_	