## wieland

# eco M58

### CuZn42 – CW510L | Lead free brass

Material designation				
EN	CuZn42			
	CW510L			
UNS	no EN standard			

Chemical compos	sition*		
Cu	58 %		
Zn	balance		
Pb	≤ 90 ppm		
*Reference values in % by weight			

#### Material properties and typical applications

Eco M58 is a lead-free material which nevertheless has good machining properties due to its microstrucutre. M58 can therefore be used as a substitute for conventional lead-containing machining brass if a lead content of  $\leq$  90 ppm is necessary and the requirements regarding mechanical properties and corrosion resistance are not too high.

The material composition meets the requirements of the CPSIA.

Physical properties*					
Electrical	MS/m	13,9			
conductivity	%IACS	24			
Thermal conductivity	W/(m·K)	139			
Thermal expansion					
coefficient					
(0-300 °C)	10 <sup>-6</sup> /K	21.7			
Density	g/cm³	8.36			
Moduls of elasticity	GPa	107			
*Reference values at room temperature					

Corrosion resistance

compounds.

consideration.

Machining brass is generally quite resistant against organic substances as well as neutral or alkaline

Stress corrosion cracking should be taken into account, especially in an ammoniacal atmosphere and whilst under mechanical stress. Dezincification in warm, acidic waters should also be taken into

### Types of delivery

The BU Extruded Products supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

Fabrication properties	S	
Forming		Surface treat
Machinability (CuZn39Pb3 = 100 %)	50 %	Polishing
Capacity for being cold worked	poor	mechanical electrolytic
Capacity for being hot worked	excellent	Electroplating
Joining		Heat treatme
Resistance welding (butt weld)	fair	Melting range
Inert gas shielded arc welding	fair	Hot working
Gas welding	fair	Soft annealin
Hard soldering	excellent	Thermal stress relievin
Soft soldering	excellent	

Surface treatment	
Polishing	
mechanical electrolytic	good poor
Electroplating	excellent
Heat treatment	
Melting range	870–900 °C
Hot working	650–750 °C
Soft annealing	450–550 °C 1–3 h
Thermal stress relieving	200–350 °C 1–3 h

Product standards	;
Rod	EN 12164
	EN 12165
Wire	EN 12166
Section	EN 12167
Hollow Rod	EN 12168

# wieland ecoline

## eco M58 CuZn42 – CW510L Lead free brass

#### Mechanical properties according to EN

Temper	emper Diameter Width across flats mm mm		Tensile strength $R_m$ Yield strength $R_{p0.2}$		Elongation %			Hardness					
			MPa MP	MPa	MPa		A11.3	А	НВ				
	from	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.
M	ć	all		all	as manufactured – without specified mechanical properties				s				
R360	6	80	5	60	360	-	320	-	15	20	_	-	
H090	6	80	5	60	-	-	-	-	-	-	90	125	
R430	2	40	2	35	430	220	-	6	8	10	-	-	
H110	2	40	2	35	-	-	-	-	-	-	110	160	
R500	2	14	2	10	500	350	-	-	3	5	-	-	
H135	2	14	2	10	_	_	-	_	_	_	135	-	

Round wires acc. to EN 12166											
Temper Diameter			Tensile strength R <sub>m</sub> Yiel		Yield strength R <sub>p0.2</sub>		Elongation %			Hardness	
	mm		MPa	MPa		A100	A11.3	1.3 A	НВ		
	from	to	min.	min.	max.	min.	min.	min.	min.	max.	
Μ		all	as manufactured – without specified mechanical properties								
R360	6	20	360	-	320	-	15	20	_	_	
H095	6	20	-	-	-	-	-	-	95	130	
R430	0.5	14	430	220	-	6	8	10	_	_	
H115	1.5	14	-	-	-	-	-	-	115	170	
R500	0.5	8	500	350	-	2	5	-	-	-	
H145	1.5	8	-	-	-	-	-	-	145	-	

Wieland-Werke AG | Graf-Arco-Straße 36 | 89079 Ulm | Germany info@wieland.com | wieland.com