

## eco SW5

### CuZn21Si3P | Lead-free special brass

#### Material designation

EN	CW724R CuZn21Si3P
UNS	C69300

#### Chemical composition<sup>1</sup>

Cu	76 %
Si	3,3 %
Р	0,05 %
Zn	Rest
Pb	max. 0,0500 %

<sup>&</sup>lt;sup>1</sup>Reference values in % by weight

#### Material properties and typical applications

eco SW5 is a lead-free special brass resisting high load and exhibiting good corrosion resistance as well as excellent machinability. This alloy is suited to the production of machined and drop forged parts. eco SW5 is available as machining rod and in hot stamping quality and is designed for applications where high strength is needed. With its lead content not exceeding 500 ppm, it meets the requirements of Entry 63 in Annex XVII of the Reach Regulation. eco SW5 is used, among other things, for jewellery and watch parts and for the production of other consumer products.

The material is lead-free according to RoHS and ELV.

#### Physical properties<sup>2</sup>

Electrical conductivity	MS/m %IACS	4,5 7,8
Thermal conductivity	W/(m·K)	35
Density	g/cm³	8,25
Moduls of elasticity	GPa	~ 100

<sup>&</sup>lt;sup>2</sup>Reference values at room temperature

#### Types of delivery

The BU Extruded Products supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

#### Corrosion resistance<sup>3</sup>

Special brass generally exhibits good corrosion resistance due to alloying additions. The addition of silicon increases the tarnish resistance and the sensitivity to stress corrosion cracking and dezincification is reduced.

raprication properties			
Forming		Surface treatment	t <sup>4</sup>
Machinability (CuZn39Pb3 = 100 %)	80 %	Polishing	
Capacity for being cold worked	good	mechanical electrolytic	good poor
		Electroplating	good
Capacity for being hot worked	excellent	<sup>4</sup> for further fabrication your contact person.	properties, please call
Joining		Heat treatment	
Resistance welding (butt weld)	good	Melting range	860 – 925 °C
Inert gas shielded arc welding	good	Hot working	680 – 750 °C
Gas welding	good	Callanani	550 – 580 °C
Hard soldering	good	Soft annealing	1 - 3 h
Soft soldering	good		

#### Product standards

Rod	EN 12163
	EN 12164
	EN 12165
Wire	EN 12166
Section	EN 12167

#### Trademarks

### wieland ecoline

<sup>&</sup>lt;sup>3</sup>Reference values

# eco SW5

## CuZn21Si3P | Lead-free special brass

Mechani	cal prop	oerties	according	g to EN								
Round rods/polygonal rods acc. to EN 12163												
Temper			Width a	cross flats	Tensile strength R <sub>m</sub>	Yield str	Yield strength R <sub>p0.2</sub>		ation %		Hardness	
			mm		MPa	MPa			A100 A11.3		НВ	
	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.
М	ā	all		all	as manufa	actured – wi	ithout specifie	ed mecha	anical pr	operties	5	
R500	6	80	35	80	500	_	450	_	13	15	-	_
H130	6	80	35	80	_	-	-	-	-	-	130	180
R600	10	40	15	40	600	300	_	_	_	12	_	_
H150	10	40	15	40	-	-	-	-	-	-	150	220
R670	2	20	2	15	670	400	_	8	9	10	_	_
H170	2	20	2	15	-	-	-	-	-	-	170	-

Round ro	ods/pol	ygonal	rods							a	cc. to El	N 12164
Temper	Diameter		ameter Width across flats		Tensile strength R <sub>m</sub>	Tensile strength $R_m$ Yield strength $R_{p0.2}$		Elonga	ation %		Hardness	
mm		mm N		MPa	MPa	1Pa		A11.3	Α	НВ		
	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.
М	ć	all all		all	as manufactured – without specified mechanical properties					5		
R500	6	80	35	80	500	_	450	-	_	15	-	-
H130	6	80	35	80	-	-	-	_	_	-	130	180
R600	10	40	15	40	600	300	_	_	_	12	_	_
H150	10	40	15	40	-	-	-	-	-	-	150	220
R670	2	20	2	15	670	400	_	8	9	10	_	-
H170	2	20	2	15	-	_	-	-	-	-	170	-

Rectangular rods acc. to EN 12167											
Temper	Thickness	S	Tensile strength R <sub>m</sub>	Yield st	rength R <sub>p0.2</sub>	Elong	ation %		Hardr	Hardness	
	mm		MPa	MPa	MPa		A11.3	Α	НВ	НВ	
	from	to	min.	min.	max.	min.	min.	min.	min.	max.	
М		all	as manu	as manufactured – without specified mechanical properties							
R500	2	20	500	_	450	12	13	15	_	_	
H130	2	20	_	-	-	-	-	-	130	170	
R600	2	20	600	300	_	_	11	12	_	_	
H150	2	20	-	-	-	-	-	-	150	190	
R670	2	7	670	400	_	8	9	10	-	_	
H170	2	7	-	-	-	-	-	-	170	220	

Round w	/ires							a	cc. to EN	V 12166	
Temper	Diameter		Tensile strength R <sub>m</sub>	Yield st	rength R <sub>p0.2</sub>	Elong	ation %		Hardr	Hardness	
	mm		MPa	MPa		A100	A11.3	Α	НВ	НВ	
	from	to	min.	min.	max.	min.	min.	min.	min.	max.	
М		all	as manu	as manufactured – without specified mechanical propertie					S		
R500	0.5	20	500	_	450	12	13	15	-	_	
H110	1.5	20	-	-	_	-	-	-	110	170	
R600	0.5	8	600	300	_	10	11	12	_	_	
H130	1.5	8	_	-	-	-	-	-	130	190	
R670	0.5	8	670	400	_	8	9	10	_	_	
H160	1.5	8	-	-	-	-	_	-	160	220	
R750	0.5	8	750	450	_	2	3	_	_	_	
H200	1.5	8	-	-	-	_	-	_	200	-	