

# Wieland-SW1

CuZn21Si3P | Lead-free special brass

## Material designation

EN	CuZn21Si3P CW724R
UNS	C69300

## Chemical composition\*

Cu	76 %
Si	3 %
P	0.05 %
Zn	balance
Pb	max. 0.09 %

\*Reference values in % by weight

## Physical properties\*

Electrical conductivity	MS/m %IACS	4.5 7.8
Thermal conductivity	W/(m·K)	35
Density	g/cm <sup>3</sup>	8.25
Modulus of elasticity	GPa	approx. 100

\*Reference values at room temperature

## Corrosion resistance

Special brass generally exhibits good corrosion resistance due to alloying additions. The addition of silicon improves resistance to tarnishing and reduces the risk to stress corrosion cracking and dezincification. For operations at temperatures >600 °C we recommend a heat treatment at 550–580 °C for 2–3 hours to optimise corrosion resistance.

## Product standards

Rod	EN 12163 EN 12164
Wire	EN 12166
Section	EN 12167

## Material properties and typical applications

**Wieland-SW1** is according to ELV and RoHs a lead-free special brass resisting high load and exhibiting good corrosion resistance as well as excellent machinability. This alloy is suited to the production of machined and drop forged parts. ECOBRASS is available as machining brass as well as in hot stamping quality. This material is also marketed under the designation CUPHIN for sanitary applications. The material meets the requirements of ISO 6509 regarding the dezincification resistance.

Material accepted for products in contact with drinking water as per 4 MS positive list.

The material is lead free according to RoHS and ELV.

## Types of delivery

The BU Extruded Products supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

## Fabrication properties

### Forming

Machinability (CuZn39Pb3 = 100 %)	80 %
Capacity for being cold worked	good
Capacity for being hot worked	excellent*

### Joining

Resistance welding (butt weld)	good*
Inert gas shielded arc welding	good*
Gas welding	good*
Hard soldering	good*
Soft soldering	good

\*see section „Corrosion resistance“

### Surface treatment

Polishing	
mechanical	good
electrolytic	poor
Electroplating	good*

\*for further fabrication properties, please contact our Technical Marketing

### Heat treatment

Melting range	860–925 °C
Hot working	680–750 °C
Soft annealing	550–580 °C 1–3 h

## Trademarks



Further information is provided in our brochure on Ecobass.

# Wieland-SW1

CuZn21Si3P | Lead-free special brass

## Mechanical properties according to EN

Round rods/polygonal rods													acc. to EN 12163	
Temper	Diameter		Width across flats		Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Hardness			
	mm		mm		MPa	MPa		A100	A11.3	A	HB			
	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.		
M	all		all		as manufactured – without specified mechanical properties									
R500	6	80	35	80	500	–	450	–	13	15	–	–		
H130	6	80	35	80	–	–	–	–	–	–	130	180		
R600	10	40	15	40	600	300	–	–	–	12	–	–		
H150	10	40	15	40	–	–	–	–	–	–	150	220		
R670	2	20	2	15	670	400	–	8	9	10	–	–		
H170	2	20	2	15	–	–	–	–	–	–	170	–		

Round rods/polygonal rods													acc. to EN 12164	
Temper	Diameter		Width across flats		Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Hardness			
	mm		mm		MPa	MPa		A100	A11.3	A	HB			
	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.		
M	all		all		as manufactured – without specified mechanical properties									
R500	6	80	35	80	500	–	450	–	–	15	–	–		
H130	6	80	35	80	–	–	–	–	–	–	130	180		
R600	10	40	15	40	600	300	–	–	–	12	–	–		
H150	10	40	15	40	–	–	–	–	–	–	150	220		
R670	2	20	2	15	670	400	–	8	9	10	–	–		
H170	2	20	2	15	–	–	–	–	–	–	170	–		

Rectangular rods											acc. to EN 12167	
Temper	Thickness		Tensile strength R <sub>m</sub>		Yield strength R <sub>p0.2</sub>		Elongation %			Hardness		
	mm		MPa		MPa		A100	A11.3	A	HB		
	from	to	min.	min.	max.	min.	min.	min.	min.	max.		
M	all		as manufactured – without specified mechanical properties									
R500	2	20	500	–	450	12	13	15	–	–		
H130	2	20	–	–	–	–	–	–	130	170		
R600	2	20	600	300	–	–	11	12	–	–		
H150	2	20	–	–	–	–	–	–	150	190		
R670	2	7	670	400	–	8	9	10	–	–		
H170	2	7	–	–	–	–	–	–	170	220		

Round wires											acc. to EN 12166	
Temper	Diameter		Tensile strength R <sub>m</sub>		Yield strength R <sub>p0.2</sub>		Elongation %			Hardness		
	mm		MPa		MPa		A100	A11.3	A	HB		
	from	to	min.	min.	max.	min.	min.	min.	min.	max.		
M	all		as manufactured – without specified mechanical properties									
R500	0.5	20	500	–	450	12	13	15	–	–		
H110	1.5	20	–	–	–	–	–	–	110	170		
R600	0.5	8	600	300	–	10	11	12	–	–		
H130	1.5	8	–	–	–	–	–	–	130	190		
R670	0.5	8	670	400	–	8	9	10	–	–		
H160	1.5	8	–	–	–	–	–	–	160	220		
R750	0.5	8	750	450	–	2	3	–	–	–		
H200	1.5	8	–	–	–	–	–	–	200	–		