

# Wieland-Z14

CuZn37Pb2 | Machining brass

## Material designation

EN	CuZn37Pb2 CW606N
UNS	C35300

## Chemical composition\*

Cu	61.5 %
Pb	2 %
Zn	balance

\*Reference values in % by weight

## Physical properties\*

Electrical conductivity	MS/m	14
	%IACS	24
Thermal conductivity	W/(m·K)	105
Thermal expansion coefficient (0–300 °C)	10 <sup>-6</sup> /K	20.4
Density	g/cm <sup>3</sup>	8.45
Modulus of elasticity	GPa	105

\*Reference values at room temperature

## Corrosion resistance

Machining brass is generally quite resistant against organic substances as well as neutral or alkaline compounds.

Stress corrosion cracking should be taken into account, especially in an ammoniacal atmosphere and whilst under mechanical stress.

Dezincification in warm, acidic waters should also be taken into consideration.

## Product standards

Rod	EN 12164
Wire	EN 12166
Section	EN 12167
Hollow rod	EN 12168

## Material properties and typical applications

Wieland-Z14 is a material which has been successfully used in the UK. It has both good machining and good cold working properties.

## Types of delivery

The BU Extruded Products supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

## Fabrication properties

### Forming

Machinability (CuZn39Pb3 = 100 %)	85 %
Capacity for being cold worked	fair
Capacity for being hot worked	excellent

### Joining

Resistance welding (butt weld)	fair
Inert gas shielded arc welding	poor
Gas welding	poor
Hard soldering	fair
Soft soldering	excellent

### Surface treatment

Polishing	
mechanical	good
electrolytic	fair
Electroplating	excellent

### Heat treatment

Melting range	885–910 °C
Hot working	650–750 °C
Soft annealing	450–650 °C 1–3 h
Thermal stress relieving	200–300 °C 1–3 h

## Trademarks



Further information is provided in our brochure on Wiconnec.

# Wieland-Z14

CuZn35Pb2 | Machining brass

## Mechanical properties according to EN

Round rods/polygonal rods												acc. to EN 12164	
Temper	Diameter		Width across flats		Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Hardness		
	mm		mm		MPa	MPa		A100	A11.3	A	HB		
	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.	
M	all		all		as manufactured – without specified mechanical properties								
R340	10	80	10	60	340	–	280	–	–	20	–	–	
H070	10	80	10	60	–	–	–	–	–	–	70	120	
R400	2	25	2	20	400	200	–	4	8	12	–	–	
H100	2	25	2	20	–	–	–	–	–	–	100	140	
R480	2	14	2	10	480	350	–	3	5	8	–	–	
H125	2	14	2	10	–	–	–	–	–	–	125	–	

Rectangular rods												acc. to EN 12167	
Temper	Thickness			Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Hardness			
	mm			MPa	MPa		A100	A11.3	A	HB			
	from	to		min.	min.	max.	min.	min.	min.	min.	max.		
M	all			as manufactured – without specified mechanical properties									
R340	3	20		340	–	280	10	15	20	–	–		
H070	3	20		–	–	–	–	–	–	70	120		
R400	3	10		400	200	–	4	8	12	–	–		
H100	3	10		–	–	–	–	–	–	100	140		
R480	3	10		480	350	–	2	5	8	–	–		
H125	3	10		–	–	–	–	–	–	125	–		

Round wires												acc. to EN 12166	
Temper	Diameter			Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Hardness			
	mm			MPa	MPa		A100	A11.3	A	HB			
	from	to		min.	min.	max.	min.	min.	min.	min.	max.		
M	all			as manufactured – without specified mechanical properties									
R340	0.5	20		340	–	280	10	15	20	–	–		
H080	1.5	20		–	–	–	–	–	–	80	130		
R400	0.5	14		400	200	–	4	8	12	–	–		
H100	1.5	14		–	–	–	–	–	–	100	150		
R480	0.5	8		480	350	–	2	5	–	–	–		
H135	1.5	8		–	–	–	–	–	–	135	–		