

Wieland-Z12

CuZn35Pb2 | Machining brass

Material designation

| | |
|-----|---------------------|
| EN | CuZn35Pb2 CW601N |
| UNS | C34200/C34500 |

Chemical composition*

| | |
|----|---------|
| Cu | 63 % |
| Pb | 2 % |
| Zn | balance |

*Reference values in % by weight

Physical properties*

| | | |
|--|---------------------|------|
| Electrical conductivity | MS/m | 14.7 |
| | %IACS | 25 |
| Thermal conductivity | W/(m·K) | 116 |
| Thermal expansion coefficient (0–300 °C) | 10 ⁻⁶ /K | 20.4 |
| Density | g/cm ³ | 8.46 |
| Modulus of elasticity | GPa | 105 |

*Reference values at room temperature

Corrosion resistance

Machining brass is generally quite resistant against organic substances as well as neutral or alkaline compounds.

Stress corrosion cracking should be taken into account, especially in an ammoniacal atmosphere and whilst under mechanical stress.

Dezincification in warm, acidic waters should also be taken into consideration.

Product standards

| | |
|------------|----------|
| Rod | EN 12164 |
| Wire | EN 12166 |
| Section | EN 12167 |
| Hollow rod | EN 12168 |
| Tube | EN 12449 |

Material properties and typical applications

Wieland-Z12 is a high-copper machining brass which has excellent cold working properties and can still be machined. It is ideal for producing components which are primarily coined, riveted, crimped or flanged and, to a small extent, machined.

Types of delivery

The BU Extruded Products supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

Fabrication properties

Forming

| | |
|-----------------------------------|------|
| Machinability (CuZn39Pb3 = 100 %) | 80 % |
| Capacity for being cold worked | good |
| Capacity for being hot worked | good |

Joining

| | |
|--------------------------------|-----------|
| Resistance welding (butt weld) | fair |
| Inert gas shielded arc welding | poor |
| Gas welding | poor |
| Hard soldering | fair |
| Soft soldering | excellent |

Surface treatment

| | |
|----------------|-----------|
| Polishing | |
| mechanical | good |
| electrolytic | fair |
| Electroplating | excellent |

Heat treatment

| | |
|--------------------------|---------------------|
| Melting range | 885–910 °C |
| Hot working | 700–800 °C |
| Soft annealing | 450–650 °C 1–3 h |
| Thermal stress relieving | 200–300 °C 1–3 h |

Trademarks



Further information is provided in our brochure on Wiconnec.

Wieland-Z12

CuZn35Pb2 | Machining brass

Mechanical properties according to EN

Round rods/polygonal rods acc. to EN 12164

| Temper | Diameter | | Width across flats | | Tensile strength R _m | Yield strength R _{p0.2} | | Elongation % | | | Hardness | |
|--------|----------|----|--------------------|----|---|----------------------------------|------|--------------|-------|------|----------|------|
| | mm | | mm | | MPa | MPa | | A100 | A11.3 | A | HB | |
| | from | to | from | to | min. | min. | max. | min. | min. | min. | min. | max. |
| M | all | | all | | as manufactured – without specified mechanical properties | | | | | | | |
| R340 | 10 | 80 | 10 | 60 | 340 | – | 280 | – | – | 20 | – | – |
| H070 | 10 | 80 | 10 | 60 | – | – | – | – | – | – | 70 | 120 |
| R400 | 2 | 25 | 2 | 20 | 400 | – | 200 | 4 | 8 | 12 | – | – |
| H100 | 2 | 25 | 2 | 20 | – | – | – | – | – | – | 100 | 140 |
| R480 | 2 | 14 | 2 | 10 | 480 | – | 350 | 3 | 5 | 8 | – | – |
| H125 | 2 | 14 | 2 | 10 | – | – | – | – | – | – | 125 | – |

Rectangular rods acc. to EN 12167

| Temper | Thickness | | Tensile strength R _m | Yield strength R _{p0.2} | | Elongation % | | | Hardness | | |
|--------|-----------|----|---|----------------------------------|------|--------------|-------|------|----------|------|--|
| | mm | | MPa | MPa | | A100 | A11.3 | A | HB | | |
| | from | to | min. | min. | max. | min. | min. | min. | min. | max. | |
| M | all | | as manufactured – without specified mechanical properties | | | | | | | | |
| R340 | 3 | 20 | 340 | – | 280 | 10 | 15 | 20 | – | – | |
| H070 | 3 | 20 | – | – | – | – | – | – | 70 | 120 | |
| R400 | 3 | 10 | 400 | – | 200 | 4 | 8 | 12 | – | – | |
| H100 | 3 | 10 | – | – | – | – | – | – | 100 | 140 | |
| R480 | 3 | 10 | 480 | – | 350 | 2 | 5 | 8 | – | – | |
| H125 | 3 | 10 | – | – | – | – | – | – | 125 | – | |

Tubes acc. to EN 12449

| Temper | Wall thickness | | Tensile strength R _m | Yield strength R _{p0.2} | | Elongation % | | | Hardness | | |
|--------|----------------|----|---|----------------------------------|------|--------------|------|------|----------|------|--|
| | mm | | MPa | MPa | | A100 | HV | | HB | | |
| | from | to | min. | min. | max. | min. | min. | max. | min. | max. | |
| M | – | 20 | as manufactured – without specified mechanical properties | | | | | | | | |
| R290 | – | 10 | 290 | – | 180 | 45 | – | – | – | – | |
| H060 | – | 10 | – | – | – | – | 60 | 90 | 55 | 85 | |
| R370 | – | 10 | 370 | 200 | – | 20 | – | – | – | – | |
| H085 | – | 10 | – | – | – | – | 85 | 120 | 80 | 115 | |
| R440 | – | 5 | 440 | 340 | – | 10 | – | – | – | – | |
| H115 | – | 5 | – | – | – | – | 115 | – | 110 | – | |

Round wires acc. to EN 12166

| Temper | Diameter | | Tensile strength R _m | Yield strength R _{p0.2} | | Elongation % | | | Härte | | |
|--------|----------|----|---|----------------------------------|------|--------------|-------|------|-------|------|--|
| | mm | | MPa | MPa | | A100 | A11.3 | A | HB | | |
| | from | to | min. | min. | max. | min. | min. | min. | min. | max. | |
| M | all | | as manufactured – without specified mechanical properties | | | | | | | | |
| R340 | 0.5 | 20 | 340 | – | 280 | 10 | 15 | 20 | – | – | |
| H080 | 1.5 | 20 | – | – | – | – | – | – | 80 | 130 | |
| R400 | 0.5 | 14 | 400 | – | 200 | 4 | 8 | 12 | – | – | |
| H100 | 1.5 | 14 | – | – | – | – | – | – | 100 | 150 | |
| R480 | 0.5 | 8 | 480 | – | 350 | 2 | 5 | – | – | – | |
| H135 | 1.5 | 8 | – | – | – | – | – | – | 135 | – | |

Wieland-Werke AG | Graf-Arco-Straße 36 | 89079 Ulm | Germany
 info@wieland.com | wieland.com

This printed matter is not subject to revision. No claims can be derived from it unless there is evidence of intent or gross negligence. The product characteristics are not guaranteed and do not replace our experts' advice.