

Warmpress-Brass round bars Z41

updated on: february 2019

material **Wieland Z41 / CuZn40Pb2**
 standard **EN-Nr. CW617N**
 length (mm) **3000 ± 100**

availability ● **Stock Wieland Metalix AG**
 CH-4512 Bellach
 ○ **Stock Wieland-Werke**
 DE-89269 Vöhringen

Nenn ø [mm]	Features		eddy current test	Rm [MPa]	mass (kg/m)	avail- ability					
	ISO-Tolerance [mm]	end									
5	h8	+/- 0.018	standard to DKI-Check Sheet 791	≥ 500	0.167	●					
7		sharpened / chamfered			standard to DKI-Check Sheet 791	≥ 500	0.327	●			
8							+/- 0.022	0.427	●		
9										0.541	●
10											
11							0.808	○			
13									1.128	●	
14											1.308
15							1.502	●			
16				1.709					●		
17		1.929			○						
18						2.163	●				
19				2.410				●			
20		2.670			●						
22						3.231	●				
24				3.844				○			
25		4.160			●						
26						4.512	○				
28				5.232				●			
32	h9	+/- 0.062	on request		≥ 430				6.840	●	
39	h10	+/- 0.100				10.154	●				
40				10.688				●			
44			10.681		●						
48	h11	+/- 0.160	on request	≥ 360	15.380	○					
55		+/- 0.190			19.981	●					

Further dimensions and alloys on request

This datasheet is for information only and does not represent a change to service. Apart from intent or gross negligence, we assume no liability for its accuracy. Product features are not guaranteed.